SANKHLA INDUSTRIES

Technical Specification of PVC Compound Grade: PAR 76 N

Description: PAR 76 N is lead stabilized soft, injection moulding grade for applications in the shoe industry. It is formulated with carefully selected PVC resins, Plasticizers, Stabilizers and other additives.

Properties	unit	Test Method	SI 3199 Specification	Typical value *
Specific gravity	-	ASTM D 729	1.27 ± 0.02	1.27
Shore hardness	"A"	ASTM D 2240	75 ± 2	76
Before Ageing				Typical value**
Tensile strength	N/mm ²	IS 10810 Part 7	10 (min)	21
Elongation at break	%	13 10010 Fail 1	200 (min)	320
Thermal Stability @ 200°C ± 0. 5°C	Minutes	IS 10810 Part 60	30 (min)	> 30

^{*} Data evaluated on 25x25x4mm thick compression moulded block.

Processing Techniques: PAR 76 N can be processed on any good PVC injection moulding equipment with a temperature range of 140°C - 190°C

Package Storage & Handling: PAR 76 N pellets should be packed in airtight laminated plastic bags of 25 Kg net weight and stored in a cool & dry place away from sunlight. Use of gloves and nose mask is recommended during manual handling.

Safety: PAR 76 N does not undergo hazardous decomposition under normal storage conditions. Static charges may be generated by conveying PVC pellets and, therefore, the conveying systems should be properly grounded.

Spillage: Vacuum cleaning.

Disposal: Waste PVC pellets should be disposed in accordance with local regulations.

The product is intended for industrial use only. MSDS is available on request.

Disclaimer: The above test results should be used only as a guideline. The material performance depends on different conditions of processing and fabrication. Consequently, users are advised to establish for themselves that the material is suitable for there end product requirements.

Address : Regd. Office NO 2, First Floor	SANKHLA INDUSTRIES	Website : www.sankhlaindustries.com E-mail : info@sankhlaindustries.com
Race Course Road	Phone: +91-80-22250975 / 22286099	E-mail : pvccompound@airtelmail.in
Bangalore - 560001	Fax: +91-80-22282496	E-mail : pvc_compound@vsnl.com

^{**} Data evaluated on extruded sleeve of thickness between 0.8 - 1.2 mm / 1- 2 mm thick sheets.