

SANKHLA INDUSTRIES

Technical Specification of PVC Compound

Grade: SP 00100 NL

Description: SP 00 100 NL conforms to Type ST1 Non -Lead stabilized sheathing grade of IS 5831 – 1984 for wire & cable applications. It is formulated with carefully selected PVC resins, Plasticizers, Stabilizers & other additives.

Properties	unit	Test Method	SI 2100 Specification	Typical value *
Specific gravity	-	ASTM D 729	1.44 ± 0.02	1.45
Shore hardness	"A"	ASTM D 2240	86 ± 2	86
Before Ageing			IS 5831 Specification	Typical value**
Tensile strength	N/mm ²	IS 10810 Part 7	12.5 (min)	16
Elongation at break	%		150 (min)	270
After ageing @ 80°C ± 2°C for 7 days				
Tensile strength	N/mm ²	IS 10810 Part 11	12.5 (min)	16.8
Variation in Tensile strength	%		± 20	5
Elongation at break	%		150 (min)	251
Variation in Elongation	%		± 20	- 7
Thermal Stability @ 200°C ± 0. 5°C	Minutes	IS 10810 Part 60	40 (min)	> 40
Heat Shrinkage @ 150°C ± 2°C & Duration 15 minutes				
Shrinkage	%	IS 10810 Part 12	4 (max)	2.5
Loss Of Mass In Air Oven @ 80°C ± 2°C for 7 days				
Loss Of Mass	mg/cm ²	IS 10810 Part 10	2 (max)	1.2

* Data evaluated on 25x25x4mm thick compression moulded block.

** Data evaluated on extruded sleeve of thickness between 0.8 – 1.2 mm / 1- 2 mm thick sheets.

Processing Techniques: SP 00 100 NL can be processed on any good PVC extruder with a temperature range of 140°C - 175°C and preheating the same up to 70 ° C, in humid climates, is recommended to avoid moisture bubbles on end products.

Colouring: It can be coloured with 2 to 4% Non - Lead PVC compatible masterbatches without affecting end product properties.

Package Storage & Handling: SP 00100 NL pellets should be packed in airtight laminated plastic bags of 25 Kg net weight and stored in a cool & dry place away from sunlight. Use of gloves and nose mask is recommended during manual handling.

Safety: SP 00100 NL does not undergo hazardous decomposition under normal storage conditions. Static charges may be generated by conveying PVC pellets and, therefore, the conveying systems should be properly grounded.

Spillage: Vacuum cleaning.

Disposal: Waste PVC pellets should be disposed in accordance with local regulations. The product is intended for industrial use only. MSDS is available on request.

Disclaimer: The above test results should be used only as a guideline. The material performance depends on different conditions of processing and fabrication. Consequently, users are advised to establish for themselves that the material is suitable for there end product requirements.

Address : Regd. Office NO 2, First Floor Race Course Road Bangalore - 560001	SANKHLA INDUSTRIES Phone : +91-80-22250975 / 22286099 Fax : +91-80-22282496	Website : www.sankhlaindustries.com E-mail : info@sankhlaindustries.com E-mail : pvccompound@airtelmail.in E-mail : pvc_compound@vsnl.com
---	--	---