

# SANKHLA INDUSTRIES

## Technical Specification of PVC Compound

### Grade: SP 00300 02 IS NL

**Description:** SP 00300 02 IS NL conforms to Type A Non -Lead stabilized insulation of IS 5831 – 1984 for wire & cable applications. It is formulated with carefully selected PVC resins, Plasticizers, Stabilizers & other additives.

Properties	Unit	Test Method	SI 1100 Specification	Typical value*
<b>Specific gravity</b>	-	ASTM D 729	1.44 ± 0.02	1.44
<b>Shore hardness</b>	"A"	ASTM D 2240	91 ± 2	91
<b>Before Ageing</b>			<b>IS 5831 Specification</b>	<b>Typical value**</b>
Tensile strength	N/mm <sup>2</sup>	IS 10810 Part 7	12.5 (min)	17
Elongation at break	%		150 (min)	250
<b>After ageing @ 80°C ± 2°C for 7 days</b>				
Tensile strength	N/mm <sup>2</sup>	IS 10810 Part 11	12.5 (min)	18
Variation in Tensile strength	%		± 20	5.9
Elongation at break	%		150 (min)	230
Variation in Elongation	%		± 20	- 8
<b>Thermal Stability @ 200°C ± 0. 5°C</b>	Minutes	IS 10810 Part 60	80 (min)	> 80
<b>Heat Shrinkage @ 150°C ± 2°C &amp; Duration 15 minutes</b>				
Shrinkage	%	IS 10810 Part 12	4 (max)	1.5
Volume Resistivity @ 27°C	Ohm-cm	IS 10810 Part 43	1x 10 <sup>13</sup> (min)	4 x 10 <sup>13</sup>
Volume Resistivity @ 70°C	Ohm-cm		1x 10 <sup>10</sup> (min)	5 x 10 <sup>10</sup>
<b>Loss Of Mass In Air Oven @ 80°C ± 2°C for 7 days</b>				
Loss Of Mass	mg/cm <sup>2</sup>	IS 10810 Part 10	2 (max)	1

\* Data evaluated on 25x25x4mm thick compression moulded block.

\*\* Data evaluated on extruded sleeve of thickness between 0.8 – 1.2 mm / 1- 2 mm thick sheets.

**Processing Techniques:** SP 00300 02 IS NL can be processed on any good PVC extruder with a temperature range of 140° C - 180 ° C and preheating the same up to 70 ° C is recommended to avoid moisture bubbles on end products

**Colouring:** It can be coloured with 2 to 4% Non-Lead PVC compatible masterbatches without affecting end product properties.

**Package Storage & Handling:** SP 00300 02 IS NL pellets should be packed in airtight laminated plastic bags of 25 Kg net weight and stored in a cool & dry place away from sunlight. Use of gloves and nose mask is recommended during manual handling.

**Safety:** SP 00300 02 IS NL does not undergo hazardous decomposition under normal storage conditions. Static charges may be generated by conveying PVC pellets &, therefore, the conveying systems should be properly grounded.

**Spillage:** Vacuum cleaning.

**Disposal:** Waste PVC pellets should be disposed in accordance with local regulations. The product is intended for industrial use only MSDS is available on request.

**Disclaimer:** The above test results should be used only as a guideline. The material performance depends on different conditions of processing and fabrication. Consequently, users are advised to establish for themselves that the material is suitable for there end product requirements.

Address : Regd. Office NO 2, First Floor Race Course Road Bangalore - 560001	<b>SANKHLA INDUSTRIES</b> Phone : +91-80-22250975 / 22286099 Fax : +91-80-22282496	Website : <a href="http://www.sankhlaindustries.com">www.sankhlaindustries.com</a> E-mail : <a href="mailto:info@sankhlaindustries.com">info@sankhlaindustries.com</a> E-mail : <a href="mailto:pvccompound@airtelmail.in">pvccompound@airtelmail.in</a> E-mail : <a href="mailto:pvc_compound@vsnl.com">pvc_compound@vsnl.com</a>
---	--	---